

HARDENED STEEL CUTTING DIE

Hardened Steel Cutting Die for JIS K7139 Type A2

Multipurpose Test Specimen A2 · Tensile specimen — built to JIS K7139: Plastics — Multipurpose test specimens



OVERVIEW

Solid cutting die for cutting Multipurpose Test A2 specimens to JIS K7139. The die is machined from a single piece of steel, hardened and finished with a sharp, precision cutting edge, so it holds its profile when cutting harder plastics from 0 to 5 mm thick.

KEY FEATURES

- Machined from a single piece of steel — no joints or seams in the cutting edge
- Hardened, precision-finished edge for clean, square specimen sides
- Cuts harder plastics, filled compounds and sheet from 0–5 mm thick
- Integral ejector plate releases the specimen after cutting
- Long service life; cutting edge can be re-sharpened

SPECIMEN PROFILE

Overall length (min)	150 mm
Width of ends	20.0 ± 0.2 mm
Width of narrow section	10.0 ± 0.2 mm
Length of narrow section	60.0 ± 0.5 mm
Transition radius (min)	60 mm
Gauge length	50.0 ± 0.5 mm
Recommended thickness	4.0 ± 0.2 mm

Nominal values per JIS K7139; die is cut to the standard's profile.

DIE SPECIFICATIONS

Die construction	One-piece machined steel body
Cutting edge	Hardened, precision-finished
Material thickness	0 – 5 mm
Recommended materials	Rigid & semi-rigid plastics, filled compounds, rubber, sheet & film
Specimen ejection	Integral ejector plate
Press compatibility	Manual, pneumatic & hydraulic sample-cutting presses
Cut profile	Multipurpose Test Specimen A2 per JIS K7139

APPLICATIONS

- Molded plastic resin QC
- Material datasheet property generation
- Incoming resin lot acceptance
- Polymer R&D and compound comparison

Ordering & customization: Specify the standard and specimen type, die style (ribbon steel or hardened steel), the material and thickness you cut, and your press make/model so we can match the mounting. Custom profiles, multi-cavity dies and nick/notch features are available on request.

ABOUT THE STANDARD

JIS K7139 defines multipurpose test specimens and how they are molded or machined so a single bar can serve tensile, flexural and impact tests. Type A2 has a larger shoulder radius and is preferred for specimens machined or die-cut from sheet.

Also available: Ribbon Steel version

Economical steel-rule die for rubber, elastomers and soft plastics up to 3 mm thick — same JIS K7139 Type A2 profile.

Specifications are typical and may vary by configuration; confirm at time of quote. Refer to the current edition of the standard for specimen tolerances and test procedures.
Part ref. UGC-CDH-JISK7139-TA2